



Total Quality. Assured.
TEST REPORT



中国认可
国际互认
检测
TESTING
CNAS L0220

Number: GZHT91345940

Date: Jul 07, 2025

Applicant: CORTINA N.V.
MEERSBLOEM-MELDEN 42,
9700 OUDENAARDE, BELGIUM
Attn: REBECCA/JENNY

Sample Description:

Two (2) pairs of submitted samples said to be Women's Safety low shoes in Light Blue.

Standard	: ASTM F2413-24
Size	: Womens US 8
Buyer's Name	: CORTINA NV
Ref. No	: BESTKNIT S1P (BSTKNITS1P)
Brand	: SAFETY JOGGER
Manufacturer	: CORTINA NV
Colour	: Light Blue
Vendor	: --
Supplier	: --
P.O. No.	: --

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch

Guiliang Dong
Senior Lab Manager



Page 1 Of 4

wx / lydiayang

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch
深圳天祥质量技术服务有限公司广州分公司
Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou 510730
广州市黄埔区保盈东路8号401房、501房、601房、801房、901房、1003房
Tel: +86 20 2820 9114 Postcode: 510730

www.intertek.com

检验检测专用章

SHENZHEN BRANCH

(6)

Ref. : Sole: PU/PU
Insert plate: SJ Steel Plate
Toe cap: SJ Metallic Toecap (#001)
Upper: Black/Soft Light Blue Woven fabric with Black Nasa TPU Covering Toe Area
Vamp lining: Soft Light Blue Oxy Neoprene Single
Quarter lining: Soft L. Oxy Neoprene Single
Seat region lining: Grey Suede Microfiber
Insole: Non-woven
Collar: Black Oxy Neoprene Single
Tongue: Black Nalo Mesh
Insock: Dark Grey Polyester Mesh + SJFOAM2 Industrial (PU)/SJ3FIT (REGULAR)
Country Of Origin : PU/PU
Goods Exported To : E.U./U.S.
Date Received/Date Test Started : Jul. 02, 2025
Testing Period : Jul. 02, 2025-Jul. 04, 2025
Date Final Information Confirmed: --

Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Guiliang Dong
Senior Lab Manager



Slip Resistant Footwear (SR) (ASTM F2913-24)

Conditioning Test Specimen		Test Condition	
Temperature	(23 ± 2) °C	Atmosphere	(23 ± 2) °C, (50 ± 5)% RH
Relative Humidity	(50 ± 5)% RH	Test Surface	Flat Unglazed Clay Quarry Tile
Period	At Least 3 Hours	Vertical Force	400 N

Size	Sequence	Conditions	Modes	Results (COF)	ASTM F2413-24 Requirement	Pass/Fail
8 (Left)	Dry Then Wet	Dry	Forward Heel Slip	0.56	Min. 0.40	Pass
			Backward Forepart Slip	0.52	Min. 0.40	Pass
		Wet	Forward Heel Slip	0.44	Min. 0.40	Pass
			Backward Forepart Slip	0.43	Min. 0.40	Pass
8 (Right)	Wet Then Dry	Wet	Forward Heel Slip	0.42	Min. 0.40	Pass
			Backward Forepart Slip	0.41	Min. 0.40	Pass
		Dry	Forward Heel Slip	0.52	Min. 0.40	Pass
			Backward Forepart Slip	0.47	Min. 0.40	Pass
8 (Right)	Dry Then Wet	Dry	Forward Heel Slip	0.47	Min. 0.40	Pass
			Backward Forepart Slip	0.48	Min. 0.40	Pass
		Wet	Forward Heel Slip	0.43	Min. 0.40	Pass
			Backward Forepart Slip	0.46	Min. 0.40	Pass

Note: It Must Be Noted That The Slip Resistance Test Carried Out In This Report Denotes An Indication Of Slip Of This Particular Footwear/Component On The Surface Mentioned In The Test Item. It Is Important To Note That Footwear Is Subjected To Many Different Conditions Encountered In Everyday Use And That It Is Impossible To Make Footwear Resistant To Slip In All Conditions. Nevertheless, It Is Generally Accepted That Problems Are Minimized If The Guideline Coefficients Of Friction Are Achieved.



End Of Report

The statement of conformity in this report is based on the decision rules agreed upon by the Client. Intertek has taken into account the measurement uncertainty calculated by the laboratory. This applies only where no specific decision rules are defined by the Client, regulatory requirements, or standard specifications. Please note that the applied decision rule is applicable solely to numerical test results. For any other cases where specific decision rules have been established by the Client, regulations, or standards, those rules will take precedence over the general guidelines used herein.

All samples information provided in this report was submitted by the Client. The Client is solely responsible for the accuracy and completeness of the samples and associated information. The observations and test results in this report are relevant to the sample(s) tested and submitted by client, The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. This report does not discharge or release you from your legal obligations and duties to any other person. Only the Client is authorized to permit copying or distribution of this report and the report shall not be reproduced except in full, Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek, This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

Remark:

1. As Requested by the Applicant, For Details Refer to Attached Page (S).
2. All the tested item are tested under the standard condition.
3. The report is valid with commission test only for the test samples in the case of delivering samples by clients.